

## Patent Abstracts of Japan

PUBLICATION NUMBER : 02073836  
PUBLICATION DATE : 13-03-90


APPLICATION DATE : 08-09-88  
APPLICATION NUMBER : 63225166

APPLICANT : JSP CORP;

INVENTOR : AKIYAMA HIROYUKI;

INT. CL. : C08J 9/228 B29C 45/00 // B29K105:04

TITLE : PRODUCTION OF FOAM OF INJECTION-MOLDING



**ABSTRACT :** **PURPOSE:** To obtain lightweight foam of injection molding having low density and high strength by blending expanded particles with a thermoplastic resin having a lower softening point than the particles, heating the blend at a temperature <the softening point of the particles and  $\geq$  the softening point of the resin and injection molding.

**CONSTITUTION:** Expanded particles (preferably ones having  $0.3-0.02\text{g/cm}^3$  density and 0.5-5mm average particle diameter such as polystyrene) 2 are blended with a thermoplastic resin (e.g. polycarbonate) 3 having a lower softening point, preferably  $\geq 10^\circ\text{C}$  lower than the particles in the ratio of preferably (1:99)-(50:50) and heated at a temperature <the softening point of the particles, preferably <the softening point  $-5^\circ\text{C}$  and  $\geq$  the softening point of the resin, preferably  $\geq$  the softening point  $+20^\circ\text{C}$ , injected into a mold 7 and molded to give injection molded foam (preferably one having  $0.8-0.08\text{g/cm}^3$  density). Further in order to make the foam lightweight, the blend may be mixed with a blowing agent of thermal decomposition type.

COPYRIGHT: (C) JPO

H. Bruning

Beads in Thermoplast-Schmelze & Werten

Alt

M. Ziegler